



DeWitt Pro-5

Product Specification

TYPICAL PROPERTIES

TEST METHOD

Material		Polypropylene
Color		Black with a gold Stripe every 12"
Thickness		5.0 oz (average)
Permeability		12 gal/sqft/min
Grab Tensile Strength (lbs)	ASTM D-4632	Warp – 100 Fill – 60
Grab Elongation (%)	ASTM D-4632	Warp - 23 Fill – 17
Trapezoidal Tear (lbs)	ASTM D-4533	70 / 70
Mullen Burst (psi)	ASTM D-3786	85
UV Exposure		>70% after 2500 Carbon Arc hrs
Weatherometer		(5 year minimum) FEDTM 191-70%

SPECIALTY CONSTRUCTION SUPPLY

12450 West Franklin Road
Boise, Idaho 873709
Phone (208) 322-6800
Fax (208) 322-2636

Toll Free 888-574-7732
www.specialtysupply.com

4390 N Yellowstone Hwy Suite #1
Idaho Falls, Idaho 83401
Phone (208) 522-3242
Fax (208) 522-4012