



DeWitt 12-Year Product Specification

Typical Properties

Test Method

Basis Weight

3.0 oz/SY

Grab Tensile Strength (lbs/inch)	ASTM D-4632	MD	56.5
		CD	53.5
Grab Elongation (%)	ASTM D-4632	MD	40
		CD	50
Trapezoidal Tear (lbs)	ASTM D-4533	MD	31.5
		CD	26.5
Mullen Burst (psi)	ASTM D-3786	75	
Thickness (mils)	ASTM D-1777		24.4
Permittivity (s-1)	ASTM D-4491		0.572
Permeability (cm/sec)	ASTM D-4491		0.036
Water Flow Rate	ASTM D-4491		42.8
(gal/min/ft ²)			

Product Benefits

- Hydro philic treated / allows air and water to pass through.
- Minimizes light penetration to suppress weed growth.
- Fabric is treated to minimize degradation due to UV light exposure.
- Covered (pine straw, pine bark, wood chips, etc...) fabric offers extended use, strong, durable, and resistant to damage from temperature extremes.

SPECIALTY CONSTRUCTION SUPPLY

12450 West Franklin Road
Boise, Idaho 873709
Phone (208) 322-6800
Fax (208) 322-2636

Toll Free 888-574-7732
www.specialtysupply.com

4390 N Yellowstone Hwy Suite #1
Idaho Falls, Idaho 83401
Phone (208) 522-3242
Fax (208) 522-4012